

## DESCRIPTION

JM Painted Aluminum Roll Jacketing has a factory applied and baked finish of highly durable hard film acrylic, epoxy, or polyester paint on the exterior surface. This finish provides improved aesthetics, color-coding, increased emittance, and improved corrosion protection to the aluminum jacketing used on pipe, tanks, and equipment insulation systems.

The special paints used on this jacketing are chalk and fade resistant. They exhibit better resistance to oxidation and to the effects of various corrosive environments than bare aluminum jacketing. This painted surface also resists water and fingerprint staining.

Like standard bare aluminum jacketing, JM Painted Aluminum Jacketing is a premier protective outer surface for mechanical insulation systems including those on pipe, tanks, and equipment. It protects the insulation and underlying pipe/tank from physical damage, UV exposure, corrosive atmospheres, and water.

JM Painted Aluminum Jacketing (also called cladding) is available in smooth, stucco embossed, and 3/16" corrugated (cross-crimped) finishes. For larger diameter or flat surfaces, painted deep corrugated sheets are available.

JM Painted Aluminum Jacketing comes standard with a 3-mil thick poly film moisture barrier (PFMB) heat-laminated to the interior surface to help prevent corrosion of the jacketing and the underlying metal pipe, tank, or equipment. While JM recommends the use of PFMB, JM Painted Aluminum Jacketing is also available with a thin painted on coating (washcoat) on the interior surface.

## COLORS

Standard colors for JM Painted Aluminum Jacketing are white, gray and clear epoxy coated. White, the most popular color, is stocked in the most commonly used gauges (0.016" to 0.024"). Clear is stocked in 0.016" and 0.020" gauge while grey is stocked in 0.016" gauge. Additional colors and painted gauges may be available if specified by purchaser at time of order placement but this may affect minimum quantity, lead-time, and price.

## EMITTANCE OF JM PAINTED ALUMINUM

JM Painted Aluminum Jacketing has a surface emittance as measured by ASTM C1371 of:

- All colors except clear = 0.8
- Clear epoxy coated = 0.5
- Bare aluminum = 0.1 (oxidized in service)

## COMPOSITION

Commercially pure aluminum is relatively soft and less suited for use in this application. Its strength can be greatly improved by alloying with small percentages of one or more other elements such as manganese, silicon, copper, zinc, and magnesium. Additional strength can be achieved by cold working. JM carefully screens all potential aluminum coil suppliers to assure our products have the highest quality, are corrosion resistant, and comply with all relevant standards.

JM Painted Aluminum Jacketing is typically manufactured using alloys 3105 or 3003 which have very similar composition and performance and are considered interchangeable for use as insulation jacketing. JM reserves the right to ship whichever alloy is in stock at the time of order placement. One of these two specific alloys or an alternative alloy can be specified by purchaser at time of order placement but this may affect minimum quantity, lead-time, and price.

### COMPOSITION DIFFERENCES IN ALUMINUM ALLOYS (%)

ALLOY	CU	MN	MG	ZN

# JM PAINTED ALUMINUM ROLL

## ALUMINUM METAL JACKETING

### DATA SHEET

#### LIMITATIONS ON USE

JM Painted Aluminum Jacketing is not appropriate for the following applications:

- For vertical tank insulation system applications where the outer diameter is larger than 8 ft and where a painted jacket is desired, JM painted deep corrugated aluminum sheets should be used
- For applications where a maximum resistance to fire is required, JM stainless steel jacketing should be used
- Where maximum resistance to corrosion is required, JM stainless steel jacketing (T304 or T316) should be used

#### SURFACE FINISHES

Each of the three standard surface finishes (smooth, stucco embossed, and 3/16" corrugated) is available on JM Painted Aluminum Jacketing. Each of these finishes has applications where it is recommended. For more information on finish, consult the JM data sheet on Aluminum Roll Jacketing.

#### POLYFILM MOISTURE BARRIER

Poly Film Moisture Barrier (PFMB) is an engineered three layer coextruded film of polyethylene and Surlyn\* polymers with a total film thickness of 3 mils (76 µm) that is heat laminated in the factory to the interior surface of aluminum jacketing. JM recommends the use of PFMB on all types of aluminum jacketing including Painted Aluminum to help prevent pitting, crevice, and galvanic corrosion of the interior surface of the metal jacketing and the insulated pipe, tank, or equipment. Due to its superior performance characteristics, PFMB replaces the old moisture barrier technology of 1 to 3 mil thick polykraft.

\* Surlyn is a trademark of DuPont

#### FLAMMABILITY

JM Aluminum Jacketing with a 3 mil poly film moisture barrier has been tested for flammability using the industry standard ASTM E84 test method. The results are shown below. JM would not expect Painted Aluminum Jacketing to have a significantly different flammability performance.

ASTM E84 Flame Spread Index = 0  
ASTM E84 Smoke Developed Index = 5

(Tested with exterior metal surface exposed to the flame)

#### COMPLIANCE TO STANDARDS

All Painted Aluminum Jacketing from JM complies with the applicable requirements of ASTM C1729 (Aluminum Jacketing Material Standard) which includes the strength and chemical composition requirements for compliance to ASTM B209 (Aluminum Alloy Standard).

#### RECOMMENDED THICKNESS

JM recommends that the thickness of aluminum jacketing used vary based on the outer diameter of the insulation system per the requirements of ASTM C1729. This recommended thickness is shown in the table below.

#### MINIMUM ALUMINUM JACKET THICKNESS

Outer Insulation Diameter (in)	Rigid Insulation		Non-Rigid Insulation	
	in.	mm	in.	mm
8	0.016	0.41	0.016	0.41
Over 8 thru 11	0.016	0.41	0.020	0.51
Over 11 thru 24	0.016	0.41	0.024	0.61
Over 24 thru 36	0.020	0.51	0.032	0.81
>36	0.024	0.61	0.040	1.01

Formerly Pabco/Childers Metal



717 17th St.  
Denver, CO 80202  
(800) 231-1024  
JM.com

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Regional Sales Office nearest you for current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville thermal insulation and systems, visit [www.jm.com/terms-conditions](http://www.jm.com/terms-conditions) or call (800)654-3103.